

SPS



Ironmongery

Rust-preventing primer for iron and steel.

- Good anti-corrosion properties
- Smooth brush application
- High covering power

Ironmongery

DESCRIPTION

Finess iron primer is a rust-preventing primer based on white spirit. For application on iron and steel, but also for metals that are heated, such as radiators and heating pipes. This primer is suitable for both indoors and outdoors.

RECOMMENDED SYSTEM

Substrate: The substrate must be clean, dry, dust- and grease-free. Remove rust and poorly adhering paint layers completely with a wire brush. Untreated metal: Carefully remove grease, any mill scale and rust. Treat with two coats of Finess Iron Age Primer, then apply a coat of Finess Primer and finish with Finess High Gloss or Silk Gloss. Treated metal in poor condition: Remove all poorly adhering and loose parts with paint remover, by burning or scraping off and treat as 'Untreated Metal'.

DRY TIMES BY 20° C/RH 50%

Dry to recoat: With Finess primer
Fully cured: After 7 days

RECOMMENDED WET FILM THICKNESS

75 Micron wet

RECOMMENDED DRY FILM THICKNESS

40 Micron

DIRECTIONS FOR USE

Stir well before use. If necessary, dilute the first coat with 5% white spirit. Apply two layers with a brush, paint roller or sprayer. Always apply an intermediate coat of Finess Primer before painting.

APPLICATION & THINNING: BRUSH

maximum 5 % white spirit/white spirit

APPLICATION & THINNING: ROLLER

maximum 5 % white spirit/white spirit

Date issued: 29/06/2026

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Europalaan 9
5232 BC 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu

