

SPS



ACRYL-PRIMER ISO

Sealing, water-based primer for (hard)wood

- Suitable for wood types that bleed
- Excellent flow properties
- Excellent adhesion
- Quick drying
- Virtually odourless and low solvent content

ACRYL-PRIMER ISO

DESCRIPTION

Sealing and quick drying, water-based primer for (hard) wood offering good filling performance. Prevents bleeding of hardwood and MDF. Ideal in combination with SPS water-based top coat paints. Perfectly even flow, excellent adhesion, easy to sand, and virtually odour-free. For interior and exterior use.

RECOMMENDED USE

As a base coat on untreated wood or exposed wood where sealing of water soluble substances in the substrate is required. SPS Primer ISO has a shelf life of several months after opening and can be applied to wood with a maximum moisture content of 20%.

RECOMMENDED SYSTEM

General: The surface must be capable of supporting the paint, clean, dry and free of dust or grease. Slightly round off sharp edges to obtain good edge coverage.

Exposed/untreated wood

- Prime untreated wood using SPS Primer ISO.
- Allow to dry, lightly sand and remove dust.
- Apply top coat paint.

Existing old coats

- Remove old loose coats.
- Clean the entire surface using SPS Paint cleaner.
- Sand and prime aged wood until you reach the healthy wood.
- Carry out any repairs and prime.
- Allow to dry, sand and remove dust.
- Prime exposed parts using SPS Primer ISO.
- Allow to dry, lightly sand and remove dust.
- Paint to cover.

Existing intact coats of paint

- Clean the intact coats using SPS Paint cleaner
- Sand the surface well.
- Touch up with primer or apply a complete coat of primer using SPS Primer ISO. - Allow to dry, lightly sand and remove dust.
- Apply top coat paint.

The systems described above apply for the most common types of surface. For specific applications and/or detailed advice, please contact SPS bv.

TECHNICAL DATA

Density (g/cm³):	1.35
Gloss Level:	Matt
Solids content in volume:	38%

DRY TIMES BY 20° C/RV 50%

Touch dry:	1 hour
Dry to recoat:	6 hours

RECOMMENDED WET FILM THICKNESS

80 µm

RECOMMENDED DRY FILM THICKNESS

30 µm

THEORETICAL CONSUMPTION

approx. 12-14 m² /litre per coat

PRACTICAL CONSUMPTION

The actual coverage depends on the nature and the structure of the surface and the application method.

DIRECTIONS FOR USE

DIRECTIONS FOR USE

Stir well before use. Apply in 1 or more coats using a suitable brush or paint roller. Water-based products dry relatively quickly. Always work wet-on-wet to prevent visible marks in the paint. Do not retouch when drying. Lightly sand and remove any dust between the coats.

APPLICATION CONDITIONS

Do not use at temperatures lower than +8°C. Only apply if the surface temperature is at least 3°C above the dew point temperature. Do not apply outdoors when it is likely to rain, when frost is expected or in direct sunlight. Always use the necessary personal protective equipment when applying this product. Always ventilate appropriately when applying.

REMARKS

Can be painted over after 16 hours in the case of wood types that bleed. Variations in coating thickness, temperature, humidity, etc. affect the drying time.

SAFETY DATA

VOC level:	20 g/l
VOC category:	A/d
VOC limit:	130 g/l
Remarks regarding safety:	This paint and the packaging should be disposed of at a collection point for hazardous or special waste.

PH

9.0000

SHELF LIFE

Minimum of 12 months in the tightly sealed original packaging in a dry, cool and frost-free place.

Date issued: 29/06/2022

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu



WWW.SPSBV.COM