

# SPS



## CONCRETE CONTACT SPRAY

**sprayable adhesive coating for stucco work.**



- For roller and spray application
- Fast-drying = time-saving
- Ready to use
- Excellent adhesion
- Alkali-resistant

# CONCRETE CONTACT SPRAY

## ОПИСАНИЕ

Roller and sprayable, pink-coloured, alkali-resistant primer based on acrylic resin. Forms a bonding bridge on substrates, on which a finishing coat of gypsum cannot be applied directly. For interior use.

## ПРЕПОРЪЧИТЕЛНА УПОТРЕБА

As an adhesion promoter on untreated, smooth and dense, weakly or nonabsorbent mineral substrates. Suitable for pre-treatment of dense, non-absorbent or poorly absorbent, untreated (prefabricated) concrete and concrete enamel.

## ПРЕПОРЪЧИТЕЛНА СИСТЕМА

Existing load-bearing substrates - Carry out any repairs. - Pre-treatment with SPS Concrete Contact Spray. Contamination by nicotine, moisture, rust or soot - Clean thoroughly. - Repair if necessary. - Pre-treat the entire surface with SPS Iso-Primer. - After drying pretreat with SPS Concrete Contact Spray. The above systems apply as a general description for most common substrates. For specific applications and/or detailed advice, please contact SPS bv.

## ТЕХНИЧЕСКИ ДАННИ

Плътност (г/см<sup>3</sup>): 1.6  
Съдържание на сухо вещество (по обем): 25 %

## ВРЕМЕ ЗА СУШЕНЕ ДО 20° C/RH 50%

Сух на допир: 2 hours.  
Готов за повторно нанасяне: 4 hours

## МОКЪР СЛОЙ

Apply 1 thin layer, not excessively.

## РАЗХОДНА НОРМА

With spray application: 120-150gr/m<sup>2</sup> per coat.  
With roller: 100-120gr/m<sup>2</sup> per coat.

## КОНСУМАЦИЯ

Actual consumption depends on the nature and structure of the substrate and the processing method.

## ПОДГОТОВКА НА ПОВЪРХНОСТТА

The substrate must be, load-bearing, fully bonded, clean, dry, dust- and grease-free. Repair cracks and fissures. Remove and/or repair loose and unstable layers.

## НАЧИН НА УПОТРЕБА

SPS Concrete Contact Spray is ready-to-use. Stir well before use. Apply evenly in 1 layer with a brush, roller or sprayer.

## УСЛОВИЯ ЗА НАНАСЯНЕ

Do not apply at temperatures below 8°C or above 30°C. Apply only when the temperature of the substrate is at least 3°C above the dew point temperature.

## НАНАСЯНЕ И РАЗРЕЖДАНЕ: ЧЕТКА

Ready-to-use.

## НАНАСЯНЕ И РАЗРЕЖДАНЕ: ВАЛЯК

Ready-to-use.

## БЕЗВЪЗДУШНО ПРЪСКАНЕ (AIRLESS SPRAY)

Airless: Nozzle: 0.015" - 0.017", Pressure: 75 - 100 bar.  
The specified settings for spraying this product are a starting point. Depending on site conditions, settings will have to be determined by the applicator.

## ПОЧИСТВАНЕ НА ОБОРУДВАНЕ И РАЗЛИВИ

With clean water.

## ЗАБЕЛЕЖКИ

Before use, consult the plaster supplier's instructions for the correct plaster and correct application.

## СРОК НА ГОДНОСТ

Minimum 12 months in tightly closed original container in dry, cool and frost-free place.

Дата на издаване: 20/04/2026

**Налични цветове и размери на опаковките:** Моля, вижте съответната продуктова страница на [www.rust-oleum.eu](http://www.rust-oleum.eu), за да се запознаете с актуалните налични цветове и размери на опаковките.

**Отказ от отговорност:** Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоятелно в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случайни щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителите е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение безплатно и могат да бъдат изтеглени от [www.rust-oleum.eu](http://www.rust-oleum.eu) или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя свойствата на своите продукти без предварително уведомление.

**Rust-Oleum Netherlands B.V.**  
Europalaan 9  
5232 BC 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

