

SPS



CONCRETE CONTACT SPRAY

sprayable adhesive coating for stucco work.



- For roller and spray application
- Fast-drying = time-saving
- Ready to use
- Excellent adhesion
- Alkali-resistant

CONCRETE CONTACT SPRAY

DESCRIPTION

Roller and sprayable, pink-coloured, alkali-resistant primer based on acrylic resin. Forms a bonding bridge on substrates, on which a finishing coat of gypsum cannot be applied directly. For interior use.

RECOMMENDED USE

As an adhesion promoter on untreated, smooth and dense, weakly or nonabsorbent mineral substrates. Suitable for pre-treatment of dense, non-absorbent or poorly absorbent, untreated (prefabricated) concrete and concrete enamel.

RECOMMENDED SYSTEM

Existing load-bearing substrates - Carry out any repairs. - Pre-treatment with SPS Concrete Contact Spray. Contamination by nicotine, moisture, rust or soot - Clean thoroughly. - Repair if necessary. - Pre-treat the entire surface with SPS Iso-Primer. - After drying pretreat with SPS Concrete Contact Spray. The above systems apply as a general description for most common substrates. For specific applications and/or detailed advice, please contact SPS bv.

TECHNICAL DATA

Density (g/cm³): 1.6
Solids content in volume: 25 %

DRY TIMES BY 20° C/RH 50%

Touch dry: 2 hours.
Dry to recoat: 4 hours

RECOMMENDED WET FILM THICKNESS

Apply 1 thin layer, not excessively.

THEORETICAL CONSUMPTION

With spray application: 120-150gr/m² per coat.
With roller: 100-120gr/m² per coat.

PRACTICAL CONSUMPTION

Actual consumption depends on the nature and structure of the substrate and the processing method.

SURFACE PREPARATION

The substrate must be, load-bearing, fully bonded, clean, dry, dust- and grease-free. Repair cracks and fissures. Remove and/or repair loose and unstable layers.

DIRECTIONS FOR USE

SPS Concrete Contact Spray is ready-to-use. Stir well before use. Apply evenly in 1 layer with a brush, roller or sprayer.

APPLICATION CONDITIONS

Do not apply at temperatures below 8°C or above 30°C. Apply only when the temperature of the substrate is at least 3°C above the dew point temperature.

APPLICATION & THINNING: BRUSH

Ready-to-use.

APPLICATION & THINNING: ROLLER

Ready-to-use.

APPLICATION & THINNING: AIRLESS SPRAY

Airless: Nozzle: 0.015" - 0.017", Pressure: 75 - 100 bar.

The specified settings for spraying this product are a starting point. Depending on site conditions, settings will have to be determined by the applicator.

CLEANING OF EQUIPMENT / SPILLS

With clean water.

REMARKS

Before use, consult the plaster supplier's instructions for the correct plaster and correct application.

SHELF LIFE

Minimum 12 months in tightly closed original container in dry, cool and frost-free place.

Date issued: 20/04/2026

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Europalaan 9
5232 BC 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu

