

# SPS



## MULTI-PRIMER PLUS

# Quick drying water-based primer

- Extremely good coverage
- Good filling
- Good flow
- Good edge coverage
- Matte appearance

# MULTI-PRIMER PLUS

## DESCRIPTION

Quick drying water-based primer with very good coverage, based on a tribrid technology. Very suitable as primer and adhesive primer on wood, MDF, hard plastics and non-ferrous metals (aluminium, zinc, etc.). Multi-Primer Plus is easy to sand and fits perfectly into a paint system with solvent-based and waterborne SPS paints. For interior and exterior use.

## UTILISATION RECOMMANDÉE

SPS Multi-Primer Plus is especially suited as a primer on untreated or exposed wood, plastic, non-ferrous metals indoors and exterior situations which are indirectly exposed to normal atmospheric conditions. SPS Multi-Primer Plus has excellent filling properties and is easy to sand down. The adhesion on several substrates like old coats of paint, PVC, metals etc. is outstanding. SPS Multi-Primer Plus can be finished with waterbased and solvent based opaques/laquers.

## SYSTÈME RECOMMANDÉ

**General:** The surface must be capable of supporting the paint, clean, dry and free of dust or grease. Slightly round off sharp edges to obtain good edge coverage.

**Wood, non-ferrous metals and hard plastic that have not been primed or have been sanded back to expose the base material:**

- Prime with SPS Multi-Primer Plus.
- Allow to dry, lightly sand and remove dust.
- Apply top coat paint.

### Existing old coats

- Remove old loose coats.
- Clean the entire surface using a Paint cleaner like Universol®.
- Sand decayed wood down to healthy wood before applying primer.
- Carry out any repairs and prime.
- Allow to dry, sand and remove dust.
- Prime exposed parts using SPS Multi-Primer Plus.
- Allow to dry, lightly sand and remove dust.
- Apply top coat paint.

### Existing intact coats of paint

- Clean the intact coats using a Paint cleaner like Universol®.
- Sand the surface well.
- Touch up with primer or apply a complete coat of primer using SPS Multi-Primer Plus.
- Allow to dry, lightly sand and remove dust.
- Apply top coat paint.

The systems described above apply for the most common types of surface. For specific applications and/or detailed advice, please contact SPS bv.

## DONNÉES TECHNIQUES

|                        |      |
|------------------------|------|
| Densité (g/cm³):       | 1.45 |
| Extrait sec en volume: | 40%  |

## TEMPS DE SÉCHAGE À 20°C/HR 50%

|              |         |
|--------------|---------|
| Au toucher:  | 1 hour  |
| Recouvrable: | 6 hours |

## EPAISSEUR DE FILM HUMIDE RECOMMANDÉE

80 µm

## EPAISSEUR DE FILM SEC RECOMMANDÉE

30 µm

## CONSUMMATION THÉORIQUE

12-14 m²/liter per layer

## CONSUMMATION PRATIQUE

The actual coverage depends on the nature and the structure of the surface and the application method.

## PRÉCAUTIONS D'UTILISATION

Stir well before use. This product is ready for use and needs no dilution. Apply evenly in 1 or 2 (untreated wood) coats using a suitable brush or paint roller at the recommended film thickness. After drying sand lightly with a grain size of >P280 and clean away the dust. After that finish with a SPS opaque/laquer. Water-based products dry relatively quickly. Always work wet-on-wet to prevent visible marks in the paint. Do not touch up when drying. Lightly sand and remove any dust between the coats.

## CONDITIONS D'APPLICATION

Do not apply at temperatures below +8°C. Only apply if the surface temperature is at least 3°C above the dew point temperature. Do not apply outdoors when it is likely to rain, when frost is expected or in direct sunlight. Always use the required personal protective equipment when applying this product. Always ventilate appropriately when applying. Products that contain alkyd resins can, when covered or when in dark environment, show yellowing. When exposed to daylight, this phenomenon will occur many times less.

## NETTOYAGE DU MATERIEL / ECLABOUSSURES

Use water and soap

## REMARQUES

SPS Multi-Primer Plus has the capacity to be left unfinished for about one season in exterior situations which are indirectly exposed to normal atmospheric conditions, before it is finished with a top coat. When old coats are, locally, completely removed from carpentry, the substrate has to be primed with sufficient Multi-Primer Plus because the film thickness from the factory has to be matched. BREEAM: The products of SPS bv are compliant to all legislation concerning VOC (VOC directive for paints and varnish nr 2004/42/EG) and therefore do not hold back for certification according to BREEAM-NL HEA 9. Waterborn paints contain none or almost no solvents and are less harmful to the environment. Tools can be cleaned with water. To prevent contamination and pollution, collect the rinse water and dispose via the designated (environmental) depot.

## DONNÉES DE SÉCURITÉ

|                             |                                                                                                          |
|-----------------------------|----------------------------------------------------------------------------------------------------------|
| Teneur en COV:              | 50 g/l                                                                                                   |
| Catégorie COV:              | A/d                                                                                                      |
| Limite COV:                 | 130 g/l                                                                                                  |
| Remarques pour la sécurité: | This paint and the packaging should be disposed of at a collection point for hazardous or special waste. |

## PH

9.0000

## DURÉE DE VIE

Minimum of 12 months in the tightly sealed original packaging in a dry, cool and frost-free place.

Date d'émission: 29/06/2022

**Couleurs et conditionnements disponibles:** Reportez-vous à la page produit concernée sur [www.rust-oleum.eu](http://www.rust-oleum.eu) pour avoir un aperçu des couleurs et des tailles d'emballage actuellement disponibles.

**Notion de responsabilité:** Les informations communiquées ici sont véridiques et exactes et sont fournies de bonne foi au meilleur de nos connaissances, mais sans garantie. Il est estimé que l'utilisateur se sera assuré lui-même de la compatibilité de nos produits avec son usage particulier. Rust-Oleum Europe ne sera en aucun cas tenue pour responsable quant aux dommages consécutifs ou indirects. Les produits doivent être stockés, manipulés et appliqués conformément aux conditions respectant les recommandations de Rust-Oleum Europe détaillées dans le dernier exemplaire de la fiche technique du produit. Il incombe aux utilisateurs de veiller à disposer de l'exemplaire actuel. Les dernières versions de la fiche technique du produit sont disponibles gratuitement et peuvent être téléchargées sur [www.rust-oleum.eu](http://www.rust-oleum.eu) ou sur demande adressée à notre département Service à la clientèle. Rust-Oleum Europe se réserve le droit de modifier les propriétés de ses produits sans avis préalable.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)



[WWW.SPSBV.COM](http://WWW.SPSBV.COM)