



# SPS



## RENOCRYL ROOF

# Roof renovation paint based on 100% acrylate

- Colourfast and UV-resistant
- Permanently elastic
- Breathable
- Easy to apply
- Excellent adhesion

# RENOCRYL ROOF

## DESCRIPTION

Light silk-gloss, high-quality roof renovation paint based on 100% acrylate. The product makes old pitched roofs look like new again and extends their lifespan. Excellent adhesion and easy to apply. Provides long-term protection for concrete tiles, fibre cement slates or corrugated sheet against harmful weather influences, moss, mould, algae growth and acid rain. For exterior use.

## RECOMMENDED USE

Outdoor application on weathered sloping roofs. Gives long-term protection to cement tiles, fibre cement slates or corrugated sheets against weathering, moss, mould, algae growth and acid rain.

## RECOMMENDED SYSTEM

Check substrate for defects and/or leaks. Remove all loose parts with a wire brush or by scraping off with a putty knife. Then thoroughly clean with pressure washer or mechanically, so that all dirt, salt deposits, grease, dust, algae and moss are removed. Then rinse well with clean water and allow to dry. Avoid too long a period between cleaning and application of Renocryl Roof (max. 3 weeks). If the surface is highly absorbent and/or powdery, apply SPS Fix-Primer. The above is a general description. For specific applications and/or detailed advice, please contact SPS bv.

## TECHNICAL DATA

Density (g/cm <sup>3</sup> ):	1,25
Gloss Level:	sps_zijdeglans
Gloss level at 60°:	satin.
Solids content in volume:	38%

## DRY TIMES BY 20° C/RH 50%

Touch dry:	2 hours.
Dry to recoat:	6 - 12 hours.

## RECOMMENDED WET FILM THICKNESS

170 - 210 micrometres.

## RECOMMENDED DRY FILM THICKNESS

65 - 80 micrometres.

## THEORETICAL CONSUMPTION

2 - 2.5 m<sup>2</sup>/l/coat.

## PRACTICAL CONSUMPTION

Actual consumption depends on the nature and structure of the substrate and the processing method.

## SURFACE PREPARATION

The substrate must be load-bearing, completely sealed, clean, dry, dust- and grease-free. Repair cracks and fissures. Remove and/or repair loose and unstable layers. For exterior use, remove all algae and moss growth.

## DIRECTIONS FOR USE

Stir well before use. Always apply in 2 layers with a brush, roller or airless sprayer. Dilute the first layer with 10% water, depending on the absorbency of the substrate. Airless spray: dilute the first coat approx. 10% with water. After approx. 1 hour drying (depending on outdoor temperature) of the first coat, apply the second coat undiluted. Always work wet-on-wet when spraying.

## APPLICATION CONDITIONS

Do not apply at temperatures below +8°C. Only apply when the temperature of the substrate is at least 3°C above the dew point temperature. Do not apply outdoors under threat of rain, frost, or in full sunlight.

## APPLICATION & THINNING: BRUSH

Maximum 10% water (first layer).

## APPLICATION & THINNING: ROLLER

Maximum 10% water (first layer).

## APPLICATION & THINNING: AIRLESS SPRAY

Airless: Nozzle opening: 0.017-0.023", Pressure approx. 150 bar, Dilute max. 10% (1st layer)

The specified settings for spraying this product apply as a starting point. Depending on site conditions, settings will have to be determined by the applicator.

## CLEANING OF EQUIPMENT / SPILLS

Water and soap.

## REMARKS

The values listed in this technical data sheet are determined on the basis of DIN EN 13300. Always use the necessary personal protective equipment when handling this product. Do not inhale product vapour and spray mist. Always ventilate appropriately during application. Dispose of residues of this material and its packaging to hazardous or special waste collection point.

## SHELF LIFE

Minimum 12 months in tightly closed original container in dry, cool, frost-free place.

Date issued: 26/06/2026

**Available colours & pack sizes:** Please refer to the respective product page on [www.rust-oleum.eu](http://www.rust-oleum.eu) for an overview of actual available colours and pack sizes.

**Disclaimer:** The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from [www.rust-oleum.eu](http://www.rust-oleum.eu) or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

**Rust-Oleum Netherlands B.V.**  
Europalaan 9  
5232 BC 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zefem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

