

SPS



RESIMAT EC

Optimally cleanable, extra matt wall paint



- Optimal zu reinigen
- Extra matt
- Abperlend
- Gut deckend
- Nassabriebbeständigkeit: Klasse 1

WWW.SPSBV.COM

RESIMAT EC

BESCHREIBUNG

Optimal zu reinigende, stumpfmatte Wandfarbe auf Basis einer speziellen Bindemittelkombination. Die trockene Farbschicht hat eine abperlende Wirkung für eine verminderte Schmutzablagerung und bleibt auch nach dem Reinigen matt. In hohem Maße für die Anwendung auf Wänden in öffentlichen Gebäuden und schmutzanfälligen Räumen wie Küchen, Badezimmern und Empfangsbereichen geeignet. Für den Innenbereich.

EMPFOHLENE VERWENDUNG

as a durable and very easily cleanable, even matt finish for interior walls and ceilings. Suitable surfaces include: existing coats of wall paint, cement and plasterwork, concrete, brick, gypsum panelling, etc. Also extremely suitable for painting glass fibre fabric.

EMPFOHLENES SYSTEM

General information: The surface must be capable of supporting the paint, completely set, clean, dry, and free from dust or grease. Repair cracks and fissures. Remove and/or repair all loose and unstable coats.

New, untreated substrates - Prime highly absorbent surfaces in their entirety using SPS Stabilising primer. - Thoroughly clean powdery surfaces. Prime with Stabilising primer after allowing to dry. - After drying, apply 2 coats of SPS Resimat EC. Existing intact coats of wall paint - Clean using SPS Paint cleaner. - Apply an intermediate coat of SPS Wall Primer Extra Opaque if necessary. - After drying, apply 2 coats of SPS Resimat EC. Existing, flaking coats of wall paint - Remove loose parts. - Thoroughly wash powdery coats and allow them to dry. - Carry out any repairs. - Prime with SPS Stabilising primer. - After drying, apply 2 coats of SPS Resimat EC. Contamination caused by nicotine, damp, rust or soot - Clean thoroughly using SPS Paint cleaner. - Treat surface/stain with SPS Sealing primer. - After drying, apply 2 coats of SPS Resimat EC. The systems described above apply for the most common types of surface. For specific applications and/or detailed advice, please contact SPS bv.

TECHNISCHE DATEN

Dichte (g/cm³):	1.5
Glanzgrad:	Extra-Matt
Glanzgrad bei 85°:	1%
Feststoffgehalt in Volumen:	43%

TROCKENZEITEN BEI 20°C/RF 50%

Klebfrei:	2
Überstreichbar:	6

EMPFOHLENE NASSE SCHICHTDICKE

123 µm

EMPFOHLENE TROCKENSCHICHTDICKE

53 µm

THEORETISCHE ERGIEBIGKEIT

Approx. 8 m²/litre per coat

PRAKТИСКАЯ ПРОДУКТИВНОСТЬ

The actual coverage depends on the nature and the structure of the surface and the application method.

UNTERGRUNDVORBEREITUNG

HINWEISE ZUR VERARBEITUNG

Stir thoroughly prior to use. The first coat can be diluted with a maximum of 5% water. Apply in 1 or 2 coats using a suitable brush, paint roller or paint sprayer. For optimal cleanability, apply 2 coats. To avoid visible marks, always work wet-on-wet and distribute the paint evenly. Back-roll all overlaps in the same direction. Do not touch up when drying. Very easy to touch up after drying.

VERDÜNNUNG & ANWENDUNG: AIRLESS SPRITZEN

Nozzle opening: 0.017-0.021"

Pressure: approx. 180 bars

Air pressure: -

VERDÜNNUNG & ANWENDUNG: DRUCKLUFTSPRITZ

Nozzle opening: 0.015-0.019"

Pressure: approx. 125 bars

Air pressure: approx. 1.5 bars

REINIGUNG DER ARBEITSGERÄTE / SPRITZER

Optimal cleanability when fully cured after 30 days. The most common types of dirt are easily and effectively removed with clean, lukewarm water, possibly in combination with a mild detergent. Use a sponge or soft, non-abrasive and lint-free cloth (not a microfibre cloth). No special cleaning products are required.

BEMERKUNGEN

Rollermarkierungen sind bei dunklen Farben wahrscheinlicher, da diese das Licht absorbieren und Oberflächenfehler hervorheben. Um dies zu vermeiden, sollten der Auftrag optimalerweise im Airlessverfahren erfolgen.

PH

9

LAGERFÄHIGKEIT

Minimum of 12 months in the tightly sealed original packaging in a dry, cool and frost-free place.

Ausgabedatum: 28/11/2025

Verfügbare Farben und Packungsgrößen: Bitte beziehen Sie sich auf die jeweilige Produktseite auf www.rust-oleum.eu für eine Übersicht der aktuell verfügbaren Farben und Größen verpacken.

Haftungsausschluss: Die hierin enthaltenen Informationen wurden nach bestem Wissen wahrheitsgetreu und präzise und im guten Glauben zusammengestellt. Wir übernehmen aber keine Haftung. Wir gehen davon aus, dass sich der Anwender eigenverantwortlich über die Eignung unserer Produkte für seine individuelle Zweckbestimmung informiert hat. Rust-Oleum Europe übernimmt keinerlei Haftung für Folgeschäden oder mittelbare Schäden. Die Produkte müssen gelagert, gehandhabt und unter Bedingungen verwendet werden, die den Empfehlungen von Rust-Oleum Europe entsprechen, die in der neuesten Ausgabe des Produktdatenblatts angegeben sind. Der Anwender muss sicherstellen, dass er die neueste Ausgabe besitzt. Die neuesten Ausgaben des Produktdatenblatts können kostenlos auf www.rust-oleum.eu heruntergeladen oder bei unserer Kundendienstabteilung angefordert werden. Rust-Oleum Europe behält sich das Recht vor, die Eigenschaften seiner Produkte ohne vorherige Ankündigung zu ändern.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu



WWW.SPSBV.COM