



SPS



RESIMAT EC

Optimaal reinigbare, extra matte muurverf

- Niet opglanzend: blijft mat na reiniging
- Optimaal reinigbaar
- Extra mat
- Afparelend
- Goed dekkend

RESIMAT EC

OMSCHRIJVING

De droge verflaag heeft een afparelend effect voor verminderde vuilaanhang en is blijvend mat na reinigen. Uitermate geschikt voor toepassing op wanden in openbare gebouwen en vuilgevoelige ruimtes zoals keukens en entreehallen.

Voor binnen. Voor verwerking, optimale reinigbaarheid en verbruik kunt u het kenmerkblad raadplegen.

AANBEVOLEN GEBRUIK

as a durable and very easily cleanable, even matt finish for interior walls and ceilings. Suitable surfaces include: existing coats of wall paint, cement and plasterwork, concrete, brick, gypsum panelling, etc. Also extremely suitable for painting glass fibre fabric.

AANBEVOLEN SYSTEEM

General information: The surface must be capable of supporting the paint, completely set, clean, dry, and free from dust or grease. Repair cracks and fissures. Remove and/or repair all loose and unstable coats.

New, untreated substrates - Prime highly absorbent surfaces in their entirety using SPS Stabilising primer. - Thoroughly clean powdery surfaces. Prime with Stabilising primer after allowing to dry. - After drying, apply 2 coats of SPS Resimat EC. Existing intact coats of wall paint - Clean using SPS Paint cleaner. - Apply an intermediate coat of SPS Wall Primer Extra Opaque if necessary. - After drying, apply 2 coats of SPS Resimat EC. Existing, flaking coats of wall paint - Remove loose parts. - Thoroughly wash powdery coats and allow them to dry. - Carry out any repairs. - Prime with SPS Stabilising primer. - After drying, apply 2 coats of SPS Resimat EC. Contamination caused by nicotine, damp, rust or soot - Clean thoroughly using SPS Paint cleaner. - Treat surface/stain with SPS Sealing primer. - After drying, apply 2 coats of SPS Resimat EC. The systems described above apply for the most common types of surface. For specific applications and/or detailed advice, please contact SPS bv.

TECHNISCHE GEGEVENS

Dichtheid (g/cm³):	1.5
Glansgraad:	Extra-Mat
Glansgraad bij 85°:	1%
Vaste stof gehalte in volume:	43%

DROOGTIJDEN BIJ 20° C/RV 50%

Kleefvrij:	2
Overschilderbaar:	6

AANBEVOLEN NATTE LAAGDIKTE

123 µm

AANBEVOLEN DROGE LAAGDIKTE

53 µm

THEORETISCH VERBRUIK

Approx. 8 m²/litre per coat

PRAKTISCH VERBRUIK

The actual coverage depends on the nature and the structure of the surface and the application method.

ONDERGROND VOORBEHANDELING

INSTRUCTIES VOOR GEBRUIK

Stir thoroughly prior to use. The first coat can be diluted with a maximum of 5% water. Apply in 1 or 2 coats using a suitable brush, paint roller or paint sprayer. For optimal cleanability, apply 2 coats. To avoid visible marks, always work wet-on-wet and distribute the paint evenly. Back-roll all overlaps in the same direction. Do not touch up when drying. Very easy to touch up after drying.

VERDUNNING & APPLICATIE: AIRLESS SPUIT

Nozzle opening: 0.017-0.021"
Pressure: approx. 180 bars
Air pressure: -

VERDUNNING & APPLICATIE: LUCHTSPUIT

Nozzle opening: 0.015-0.019"
Pressure: approx. 125 bars
Air pressure: approx. 1.5 bars

REINIGEN VAN APPARATUUR / SPATTEN

Optimal cleanability when fully cured after 30 days. The most common types of dirt are easily and effectively removed with clean, lukewarm water, possibly in combination with a mild detergent. Use a sponge or soft, non-abrasive and lint-free cloth (not a microfibre cloth). No special cleaning products are required.

OPMERKINGEN

Bij donkere kleuren is de kans op rollerbanen groter door de absorptie van licht, waardoor gebreken in het oppervlak worden benadrukt. Om dit te voorkomen, geeft u de best de voorkeur aan spuitapplicatie.

PH

9

HOUDBAARHEID

Minimum of 12 months in the tightly sealed original packaging in a dry, cool and frost-free place.

Uitgiftedatum: 28/11/2025

Beschikbare kleuren en verpakkingsformaten: Raadpleeg de betreffende productpagina op www.rust-oleum.eu voor een overzicht van de actueel beschikbare kleuren en verpakkingsgrootten.

Disclaimer: De informatie in dit document is naar ons beste weten juist en wordt te goeder trouw, maar zonder garantie gegeven. De gebruiker wordt geacht onafhankelijk de geschiktheid van onze producten voor zijn/haar eigen specifieke toepassing te testen. In geen geval is Rust-Oleum Europe aansprakelijk voor directe of indirecte schade. Producten dienen te worden opgeslagen, behandeld en aangebracht volgens de aanbevelingen van Rust-Oleum Europe op het productinformatieblad (technische fiche). Het is de verantwoordelijkheid van de gebruiker om altijd de laatste versie van het productinformatieblad (technische fiche) te raadplegen en te respecteren. Deze bladen zijn gratis te downloaden van de website www.rust-oleum.eu of op aanvraag bij de afdeling Customer Service (Verkoop binnendienst). Rust-Oleum Europe houdt zich het recht voor om de eigenschappen van haar producten te wijzigen zonder voorafgaande kennisgeving.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu



WWW.SPSBV.COM