

SPS



SATIN PU-A SPRAY

Sprayable silk gloss paint based on PU-acrylate

- Scratch- and impact resistant
- Skin oils resistant
- Airless and airmix sprayable
- Great freedom of layer thickness
- Very smooth result

SATIN PU-A SPRAY

ОПИСАНИЕ

Spray system-compatible, water-based silk gloss paint based on PU-acrylate. Also ideal for application by brush in hard-to-reach areas, such as the rebate sides of tilt and turn windows. Ideal for new builds, maintenance and renovation. Good viscosity, good colour retention, perfect flow properties, creates a washable finish that is resistant to the skin's oils. For interior use.

ПРЕПОРЪЧИТЕЛНА УПОТРЕБА

SPS Satin PU A Spray can be used as a finishing layer on pre-treated substrates like wood or metal. It has very good coverage properties.

ТЕХНИЧЕСКИ ДАННИ

Плътност (г/см³):	1.2
Гланцово ниво:	sps_zijdeglans
Гланцово ниво при 60°:	35-50%
Съдържание на сухо вещество (по обем):	35%

ВРЕМЕ ЗА СУШЕНЕ ДО 20° C/RH 50%

Сух за употреба:	ca. 1 hour
Готов за повторно нанасяне:	ca. 6 hours

РАЗХОДНА НОРМА

With spraying application ca. 6 m²/L per layer. This number of paints consumption is theoretical.

КОНСУМАЦИЯ

Depending on circumstances, nature and structure of the substrate paint consumption can be different.

НАЧИН НА УПОТРЕБА

Stir very well before use. This product has light thixotropic like properties. After mixing, this product should be uniform and ready for use. Apply in 1 or 2 coats with an airmix system. Waterborn product dry relatively quick. This product can be touched up when the product is still in the wet fase. Do not touch-up during drying.

УСЛОВИЯ ЗА НАНАСЯНЕ

Do not apply when temperatures are lower than +8°C. Paint should only be applied when temperatures of the substrate are at least 3 degrees higher than dew-point. Always take necessary measures in the form of personal protective equipment (filter-mask, safetyglasses, gloves etc.) Always make sure ventilation is sufficient.

НАНАСЯНЕ И РАЗРЕЖДАНЕ: ЧЕТКА

Touch up with a brush or rollers can result in differences in structure of the paintfilm and therefor can also result in color differences with the sprayed paintfilm.

БЕЗВЪЗДУШНО ПРЪСКАНЕ (AIRLESS SPRAY)

Nozzle opening: 0.009"-0.012
Pressure: Ca. 70 bar

*With airless application, use a "low-pressure" nozzle. (Like Graco FF-LP nozzle or Wagner HEA nozzle) The proposed settings for spraying this product is a guide. Depending on circumstances these settings need to be adjusted accordingly by the applicator.

Do not spray the paint film to thick. Excessive paint film thickness will result in longer curing times, sagging and possible longer tackyness of the paintfilm. Adjust the workflow to fit the object that is to be painted.

ВЪЗДУШНО РАЗПРАШВАНЕ (AIR-ATOMISED SPRAY)

Nozzle opening: 0.009"-0.012
Pressure: Ca. 60 bar
Airpressure: 1-3 bar

Do not spray the paint film to thick. Excessive paint film thickness will result in longer curing times, sagging and possible longer tackyness of the paintfilm. Adjust the workflow to fit the object that is to be painted.

ПОЧИСТВАНЕ НА ОБОРУДВАНЕ И РАЗЛИВИ

Water and soap

ЗАБЕЛЕЖКИ

Variances in film thickness, temperature, air humidity atc. Influence drying times.

ДАНИИ ЗА БЕЗОПАСНОСТ

Ниво на ЛОС:	35 g/l
Категория ЛОС:	A/i
group_voc_40_limit:	140 g/l
Забележки относно безопасността:	See MSDS.

This paint and the packaging should be disposed of at a collection point for hazardous or special waste

PH

9

СРОК НА ГОДНОСТ

Minimum of 12 months if stored in dry, cool and frost-free storage.

Дата на издаване: 28/11/2025

Налични цветове и размери на опаковките: Моля, вижте съответната продуктова страница на www.rust-oleum.eu, за да се запознаете с актуалните налични цветове и размери на опаковките.

Отказ от отговорност: Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоятелно в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случайни щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителите е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение безплатно и могат да бъдат изтеглени от www.rust-oleum.eu или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя свойствата на своите продукти без предварително уведомление.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu



WWW.SPSBV.COM