

SPS



SATIN PU-A SPRAY

Laque satinée pistolable à base de polyuréthane-acrylate.

- Résistant aux rayures et à l'usure
- Résiste aux graisses cutanées
- Airless et airmix pistolable
- Grande liberté d'épaisseur de couche
- Résultat final très lisse

SATIN PU-A SPRAY

DESCRIPTION

Laque satinée pistolable à base aqueuse à base de polyuréthane-acrylate. Pratiquement inodore et pauvre en solvant, séchage rapide et une bonne tenue verticale. Solution idéale pour les constructions neuves, les travaux d'entretien et les rénovations. Les zones difficiles d'accès (comme les rainures des fenêtres oscillo-battantes) pendant la pulvérisation, ce produit peut également être traité parfaitement avec la brosse. Parfaite fluidité, résistance au liposome et bonne lessivabilité. Pour l'intérieur.

UTILISATION RECOMMANDÉE

SPS Satin PU A Spray can be used as a finishing layer on pre-treated substrates like wood or metal. It has very good coverage properties.

DONNÉES TECHNIQUES

Densité (g/cm³):	1.2
Niveau de brillance:	sps_zijdeglans
Niveau de brillance à 60°:	35-50%
Extrait sec en volume:	35%

TEMPS DE SÉCHAGE À 20°C/HR 50%

Manipulable:	ca. 1 hour
Recouvrable:	ca. 6 hours

CONSUMMATION THÉORIQUE

With spraying application ca. 6 m²/L per layer. This number of paints consumption is theoretical.

CONSUMMATION PRATIQUE

Depending on circumstances, nature and structure of the substrate paint consumption can be different.

PRÉCAUTIONS D'UTILISATION

Stir very well before use. This product has light thixotropic like properties. After mixing, this product should be uniform and ready for use. Apply in 1 or 2 coats with an airmix system. Waterborn product dry relatively quick. This product can be touched up when the product is still in the wet fase. Do not touch-up during drying.

CONDITIONS D'APPLICATION

Do not apply when temperatures are lower than +8°C. Paint should only be applied when temperatures of the substrate are at least 3 degrees higher than dew-point. Always take necessary measures in the form of personal protective equipment (filter-mask, safetyglasses, gloves etc.) Always make sure ventilation is sufficient.

APPLICATION & DILUTION: BROSSE

Touch up with a brush or rollers can result in differences in structure of the paintfilm and therefor can also result in color differences with the sprayed paintfilm.

APPLICATION & DILUTION: PISTOLET AIRLESS

Nozzle opening: 0.009"-0.012
Pressure: Ca. 70 bar

*With airless application, use a "low-pressure" nozzle. (Like Graco FF-LP nozzle or Wagner HEA nozzle) The proposed settings for spraying this product is a guide. Depending on circumstances these settings need to be adjusted accordingly by the applicator.

Do not spray the paint film to thick. Excessive paint film thickness will result in longer curing times, sagging and possible longer tackyness of the paintfilm. Adjust the workflow to fit the object that is to be painted.

APPLICATION & DILUTION: PISTOLET PNEUMATIQUE

Nozzle opening: 0.009"-0.012
Pressure: Ca. 60 bar
Airpressure: 1-3 bar

Do not spray the paint film to thick. Excessive paint film thickness will result in longer curing times, sagging and possible longer tackyness of the paintfilm. Adjust the workflow to fit the object that is to be painted.

NETTOYAGE DU MATERIEL / ECLABOUSSURES

Water and soap

REMARQUES

Variances in film thicknes, temperature, air humidity atc. Influence drying times.

DONNÉES DE SÉCURITÉ

Teneur en COV:	35 g/l
Catégorie COV:	A/i
Limite COV:	140 g/l
Remarques pour la sécurité:	See MSDS.

This paint and the packaging should be disposed of at a collection point for hazardous or special waste

PH

9

DURÉE DE VIE

Minimum of 12 months if stored in dry, cool and frost-free storage.

Date d'émission: 28/11/2025

Couleurs et conditionnements disponibles: Reportez-vous à la page produit concernée sur www.rust-oleum.eu pour avoir un aperçu des couleurs et des tailles d'emballage actuellement disponibles.

Notion de responsabilité: Les informations communiquées ici sont véridiques et exactes et sont fournies de bonne foi au meilleur de nos connaissances, mais sans garantie. Il est estimé que l'utilisateur se sera assuré lui-même de la compatibilité de nos produits avec son usage particulier. Rust-Oleum Europe ne sera en aucun cas tenue pour responsable quant aux dommages consécutifs ou indirects. Les produits doivent être stockés, manipulés et appliqués conformément aux conditions respectant les recommandations de Rust-Oleum Europe détaillées dans le dernier exemplaire de la fiche technique du produit. Il incombe aux utilisateurs de veiller à disposer de l'exemplaire actuel. Les dernières versions de la fiche technique du produit sont disponibles gratuitement et peuvent être téléchargées sur www.rust-oleum.eu ou sur demande adressée à notre département Service à la clientèle. Rust-Oleum Europe se réserve le droit de modifier les propriétés de ses produits sans avis préalable.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu



WWW.SPSBV.COM