

SPS



STRUKTURPUTZ BB

DECORATIVE DECORATIVE PLASTER WITH BARK EFFECT

- Excellent weather resistance
- Impact and shock resistant
- Easy to process
- Excellent adhesion
- Breathable

СТРУКТУРПУТЗ ВВ

ОПИСАНИЕ

Durable, excellent adhesion, decorative decorative plaster with bark effect, based on synthetic resin dispersion. Excellent application properties, breathable, impact-resistant and weatherproof. For interior and exterior use.

ПРЕПОРЪЧИТЕЛНА УПОТРЕБА

Suitable substrates include all smooth and flush surfaces such as: concrete, brick, cement and plaster, existing paint layers, plasterboard, fine sanding, etc.

ПРЕПОРЪЧИТЕЛНА СИСТЕМА

New, untreated substrates- Pre-treat highly absorbent substrates completely with SPS Putz-Grund. - Prime stable substrates with SPS Putz-Grund.**Existing substrates:-** Clean the substrate - Smooth and level the structured substrate - Prime stable substrates with SPS Putz-Grund.**Existing substrates with no load-bearing capacity:-** Thoroughly remove loose layers - Wash off any powdering layers thoroughly and allow to dry. - Make any necessary repairs - Pre-treat with SPS Fix-Primer - Smooth and level structured substrates - Prime stable load-bearing substrates with SPS Putz-Grund - Prime with SPS Putz-Grund.**Contamination by nicotine, moisture, rust or soot:** Thoroughly clean - Treat the surface/contamination with SPS Iso-Primer - Prime light contamination on stable load-bearing substrates with SPS Putz-Grund Iso. The above systems are general descriptions for the most common substrates. For specific applications and/or detailed advice, please contact SPS bv.

ТЕХНИЧЕСКИ ДАННИ

Плътност (г/см³): 2,0
Гланцово ниво при 60°: Matt
gloss_level_85: Matt
Съдържание на сухо вещество (по обем): 71%

ВРЕМЕ ЗА СУШЕНЕ ДО 20° C/RH 50%

Готов за повторно нанасяне: 12 hours
group_dry_40_full_cure: Some Days

РАЗХОДНА НОРМА

2 mm Medium: approx. 2.5 kg/m²

КОНСУМАЦИЯ

The stated yield is theoretical. Actual consumption depends on the nature and structure of the substrate and the processing method.

ПОДГОТОВКА НА ПОВЪРХНОСТТА

The substrate must be smooth and even. The substrate must also be load-bearing, fully bonded, clean, dry, dust- and grease-free. Tears and cracks must be repaired. Remove and/or repair loose and unstable layers. For exterior application remove all algae and moss growth. Before applying SPS ornamental plaster, pre-treat with SPS Putz-Grund. Consult the Surface Assessment Criteria for exterior plastering and the Surface Assessment Criteria for interior plastering in order to determine whether the surface is sufficiently smooth and flat to be finished with SPS ornamental plaster.

НАЧИН НА УПОТРЕБА

Pre-mix buckets together in a tub and mix well before use. If necessary, dilute with up to 5% water. Apply evenly to grain thickness with a stainless steel trowel. Then texture with a plastic trowel in a circular motion until a grooved structure appears. Texturing with a plastic trowel in vertical movements gives a bark effect. During texturing, regularly remove excess slurry from the plastic trowel.

УСЛОВИЯ ЗА НАНАСЯНЕ

Do not apply at temperatures below +8°C. Only apply when the temperature of the substrate is at least 3°C above the dew point temperature. Do not apply outdoors under threat of rain, frost, or in full sunlight.

GROUP_APPL_THINNING_50_RAKE_TROWEL

Maximum 5% clean water.

ПОЧИСТВАНЕ НА ОБОРУДВАНЕ И РАЗЛИВИ

Water and soap.

ЗАБЕЛЕЖКИ

Always use the necessary personal protective equipment when handling this product. Always ventilate appropriately during application. Slight colour deviations are possible due to the use of natural raw materials. Therefore buckets with different batch numbers must be mixed first.

СРОК НА ГОДНОСТ

Minimum 12 months in well-sealed original container in dry, cool, and frost-free place.

Дата на издаване: 17/04/2026

Налични цветове и размери на опаковките: Моля, вижте съответната продуктова страница на www.rust-oleum.eu, за да се запознаете с актуалните налични цветове и размери на опаковките.

Отказ от отговорност: Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоятелно в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случайни щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителите е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение безплатно и могат да бъдат изтеглени от www.rust-oleum.eu или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя свойствата на своите продукти без предварително уведомление.

Rust-Oleum Netherlands B.V.
Europalaan 9
5232 BC 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu

