



SPS



UNIMAT

Universally applicable wall paint

- Extra matt
- Optimal flow
- Good coverage
- Good washability
- Low odour

DESCRIPTION

Extra matt, well-covering, universal wall paint based on synthetic resin dispersion. Excellent application properties, optimal flow and breathability. Suitable for finishing walls and ceilings in dry rooms. For interior use.

RECOMMENDED USE

As a durable smooth finish on mineral substrates indoors. Suitable substrates include: existing wall paint layers, cement and plaster, concrete, brick, plasterboard, etc. Also suitable for painting glass fabric.

RECOMMENDED SYSTEM

New, untreated substrates - Prepare (strongly) absorbent substrates completely with SPS Fix-Primer. - Clean powdery substrates thoroughly. Pre-treat with Fix-Primer after drying. - Paint over **existing intact wall paints** - Thoroughly clean. - Remove loose particles. - Thoroughly wash off any powdering layers and allow to dry. - Make any necessary repairs. - Pre-treat with SPS Fix-Primer. - After drying, paint over the surface. **Contamination by nicotine, moisture, rust or soot** - Clean thoroughly. - Treat the surface/contamination with SPS Iso-Primer. - Paint over the surface after drying. The systems mentioned are general descriptions for most common substrates. For specific applications and/or detailed advice, please contact SPS bv.

TECHNICAL DATA

| | |
|-------------------------------|----------------|
| Density (g/cm ³): | 1,54 |
| Gloss Level: | Extra-Matt |
| Gloss level at 85°: | 5%, extra matt |
| Solids content in volume: | 41% |

DRY TIMES BY 20° C/RH 50%

| | |
|----------------|--------------|
| Touch dry: | 2 hours. |
| Dry to recoat: | 4 - 6 hours. |

RECOMMENDED WET FILM THICKNESS

Approx. 143 micrometres.

RECOMMENDED DRY FILM THICKNESS

Approx. 59 micrometres.

THEORETICAL CONSUMPTION

Approx. 7 m² /l per coat. The stated yield is theoretical.

PRACTICAL CONSUMPTION

Actual consumption depends on the nature and structure of the substrate and the processing method.

SURFACE PREPARATION

The substrate must be load-bearing, fully bonded, clean, dry, dust- and grease-free. Repair cracks and fissures. Remove and/or repair loose and unstable layers.

DIRECTIONS FOR USE

Stir well before use. If necessary, dilute the first coat with up to 10% water. Apply with a suitable brush, roller or sprayer. Always work wet-on-wet to avoid swelling. Re-roll all surfaces in the same direction. Do not touch up while drying.

APPLICATION CONDITIONS

Do not apply at temperatures below +8°C. Only apply when the temperature of the substrate is at least 3°C above the dew point temperature.

APPLICATION & THINNING: BRUSH

Maximum 10% water.

APPLICATION & THINNING: ROLLER

Maximum 10% water.

APPLICATION & THINNING: AIRLESS SPRAY

Airless Nozzle: 0.015"-0.017", Pressure: approx.180 bar, Dilute: Maximum 5% water.
Airmix Nozzle: 0.015-0.017", Pressure: approx.160 bar, Air pressure: approx. 1.5 bar, Dilute: Maximum 5% water.

The specified settings for spraying this product are a starting point. Depending on site conditions, settings will have to be determined by the applicator.

CLEANING OF EQUIPMENT / SPILLS

Water and soap.

REMARKS

The values listed in this technical data sheet are determined on the basis of DIN EN 13300. Always use the necessary personal protective equipment when handling this product. Do not inhale product vapour and spray mist. Always ventilate appropriately during processing. Take this material and its container to hazardous or special waste collection point.

SHELF LIFE

Minimum 12 months in tightly closed original container in dry, cool and frost-free place.

Date issued: 13/04/2026

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Europalaan 9
5232 BC 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu