

SPS



UNITEX 2525 MATT



- Super coverage
- Matt
- Economical
- Good washability
- Solvent-free and low-odour

UNITEX 2525 MATT

DESCRIPTION

Super opaque, matt wall paint based on synthetic resin dispersion. Usually covers in one coat, saving one working pass. Low-odour, breathable and washable. Particularly intended for durable finishing of interior walls and ceilings. For interior use.

RECOMMENDED USE

As a durable smooth finish on mineral substrates indoors. Suitable substrates include: existing wall paint coats, cement and plaster, concrete, brick, plasterboard, etc.

RECOMMENDED SYSTEM

New, untreated substrates - Prime highly absorbent substrates completely with SPS Fix primer. - Clean powdery substrates thoroughly. Pre-treat with SPS Fix Primer after drying. - After drying, paint over the entire surface. **Existing intact wall paint layers** - Thoroughly clean. - Paint over the surface after drying. Remove loose particles. - Thoroughly wash off any powdering layers and allow to dry. - Make any necessary repairs. - Pre-treat with SPS Fix-Primer. - Paint over the surface after drying. **Contamination by nicotine, moisture, rust or soot** - Clean thoroughly. - Treat the surface/contamination with SPS Iso-Primer. - Paint over the surface after drying. The above systems are general descriptions for most common substrates. For specific applications and/or detailed advice, please contact SPS bv.

TECHNICAL DATA

Density (g/cm ³):	1,47
Gloss Level:	Matt
Gloss level at 85°:	10%, matt.
Solids Content in weight:	35

DRY TIMES BY 20° C/RH 50%

Touch dry:	2 hours
Dry to recoat:	4 - 6 hours

THEORETICAL CONSUMPTION

Approx. 9 m² / ltr. per coat. The stated yield is theoretical.

PRACTICAL CONSUMPTION

Actual consumption depends on the nature and structure of the substrate and the processing method.

SURFACE PREPARATION

The substrate must be load-bearing, completely sealed, clean, dry, dust- and grease-free. Repair cracks and fissures. Remove and/or repair loose and unstable layers.

DIRECTIONS FOR USE

Stir well before use. If necessary, dilute the first coat with up to 10% water. Apply with a suitable brush, roller or sprayer. Always work wet-on-wet in order to avoid deposits. Re-roll all webs in the same direction. Do not touch up while drying.

APPLICATION CONDITIONS

Do not apply at temperatures below +8°C. Only apply when the temperature of the substrate is at least 3°C above the dew point temperature.

APPLICATION & THINNING: BRUSH

Maximum 10% water.

APPLICATION & THINNING: ROLLER

Maximum 10% water.

APPLICATION & THINNING: AIR-ATOMISED SPRAY

Airless Nozzle: 0.017"-0.021", Pressure: approx.200 bar, Dilute: Maximum 5% water.
Airmix Nozzle: 0.017-0.021", Pressure: approx.120 bar, Air pressure: approx. 2 bar, Dilute: Maximum 5% water.

The specified settings for spraying this product are a starting point. Depending on site conditions, settings will have to be determined by the applicator.

CLEANING OF EQUIPMENT / SPILLS

Water and soap.

REMARKS

The values listed in this technical data sheet are determined on the basis of DIN EN 13300. Always use the necessary personal protective equipment when handling this product. Do not inhale product vapour and spray mist. Always ventilate appropriately during processing. Take this material and its container to hazardous or special waste collection point.

SHELF LIFE

Minimum 12 months in tightly closed original container in dry, cool and frost-free place.

Date issued: 13/04/2026

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Europalaan 9
5232 BC 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu

